

GetPolyal

LDPEC

RECYCLED PELLETS

TECHNICAL DATA SHEET · V01 · OCTOBER 2026

Black recycled low-density polyethylene
from post-consumer film.

REFERENCE STANDARD

UNE-EN 15344

ORIGIN

Post-consumer · EU



FORMAT

Pellets

COLOUR

Black

COMPOSITION*

LDPE 97%

* Approximate contents, determined by DSC.

TECHNICAL PROPERTIES

PROPERTY	STANDARD / METHOD	TYPICAL VALUE
Melt flow index (MFI)	UNE-EN ISO 1133-1	0.7 - 1.3 g/10 min
Density	UNE-EN ISO 1183-1	0.93 - 0.95 g/cm ³
Moisture	Internal method	< 0.15 %
Ash content	UNE-EN ISO 3451	< 3 %
Vicat softening temperature	UNE-EN ISO 306	98 - 106 °C
Elongation at break	UNE-EN ISO 527	300 - 450 %

PROCESSING COMPATIBILITY

INJECTION

EXTRUSION

ROTOMOULDING

BLOW MOULDING

CAST FILM

THERMOFORMING

RECOMMENDED APPLICATIONS



Refuse sacks



Blown film



Carrier bags



Agricultural film



Shrink & pallet hood



Pipes & profiles

- Refuse sacks
- Industrial bags and medium-to-high strength sacks
- Construction film
- Industrial protective film
- Non-food agricultural film
- Mulch film
- Silage film (after UV and strength validation)
- General-purpose blown film
- Carrier bags
- Mailing and courier bags
- Industrial shrink film
- Pallet hood and wrapping film

- Blends for stretch film
- Extruded sheet for packaging, separation and protection
- Non-food packaging film
- Outer layer of non-food coextruded structures
- Non-food industrial liners
- Non-structural injection-moulded parts
- Trays, lids, protectors and spacers
- Non-critical rotomoulded products
- Profiles and protection elements
- Non-pressure pipes, ducts and profiles
- Compounds with mineral fillers, fibres or other polymers
- Plastic lumber and furniture (with specific formulation)

POSSIBLE, SUBJECT TO SPECIFIC TESTS

Stretch film as a final product · High-performance agricultural film · Injection parts with higher mechanical demands · Technical rotomoulding · Foam extrusion · Low-demand wire and cable compounds · Secondary cosmetic or pharmaceutical packaging · Packaging components without direct product contact

HOMOGENEOUS LOT

10 t

PACKAGING

Big bag 1,000 kg

SAMPLES

15 kg bag, on request

Typical values from quality control; they are not a contractual specification. Final properties depend on processing conditions. Contact us for critical applications.

MADE IN SPAIN

Recycled from post-consumer material and produced in Spain.
Traceable post-consumer recycled content.

getpolyal.com

marta@getpolyal.com

